## BCL

### High performance Cross-linked Shrink film



- Multi-layer, high clarity cross-linked Shrink film.
- Versatile film designed for a wide range of products.
- Strong seals on a wide range of sealing systems.
- High Tensile strength and tear resistance.
- Excellent machinability.







# BCL

### High performance Cross-linked Shrink film

#### **Technical Features**

Properties	125 Gauge	150 Gauge
Yield (MSI/LBS)	24	20
Gloss (45°) in %	86	85
Haze (%)	4.2	5
Free Shrink (%) @ 212° F @ 248° F	MD 16 MD 62 <sup>/</sup>	
Tensile Strength (psi)	19,580	19,580
Elongation (%)	140	145
WVTR (gm/100 sq. inch/24 hrs.)	.7	.6
O <sup>2</sup> Permeability (cc/m <sup>2</sup> /24 hrs.)	4,200	3,300
Roll Length (feet) Centerfold (CF) Singlewound (SW)	2,100 4,200	1,750 3,500
Core Internal Diameter (inch) 3"		
Nominal Outside Diameter (inch) 9.5"		
The technical features are given in good faith. It is the responsibility of the final user to verify products		

5" to 115"

5 " to 55'

All

The technical features are given in good faith. It is the responsibility of the final user to verify products suitability for all applications .Bollore maintains the right to change the definition and technical features of its products at any time.