Bolphane[®] BE

Center-folded standard multi-purpose polyolefin shrink film

OVersatility.

 Optimized pre-perforation for controlled shrinkage and easier set-up.

Strong shrink force for co-packing applications.

•Good optical properties.

Recycling Code APPLICATIONS

Bolphane BE is the standard film covering a broad spectrum of applications where a centerfolded film is required.



Its strong shrink force makes it a good candidate for multipacking applications.

Bollore, Inc. 60 Louisa Viens Dr. Dayville, CT 06241 Sales:800-343-0358 www.bolloreinc.com







Bolphane[®] BE

PRE-PERFORATION

The optimized pre-perforation of Bolphane BE allows a controlled escape of air during the shrink stage and makes the set-up easier: no more need for perforation on the shrinkwrapper.

TECHNICAL FEATURES

	e solo Lado Esclo	

Grade / Thickness	BE 50G	BE 60G	BE 75G	BE 100G	
Gloss (85° angle) in %	118				
Haze (%)	2,5			3	
Shrinkage (%) at 200° F	20				
at 250° F	50				
Seal strength (g/inch)	1 600	2 000	2 100	2 300	
WVTR (gms/100 <u>sq.in</u> ./24 hrs at 95 % HR, 95° F)	1	0.9	0.7	0.5	
O2 permeability (cc/m²/24hrs at 73° F, 1 atm)	8 500	7 000	5 500	4 000	
Roll Length (feet)	5 085	4 380	3 510	2 625	
Core Internal Diameter (inch)	3				
Nominal Roll outside Diameter (inch)	9 1/2				


PRESENTATION

Bolphane BE is available only centerfolded. Available widths : from 6" to 28" included, by increment of 1".

FOOD CONTACT APPROVAL

Bolphane ®BE complies with U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520-olefin polymer, allowing use for articles that contact food, except for articles used for packing or holding food during cooking.

PALLETIZING





Bolphane ® BE is fully recyclable in the LDPE waste stream (SPI code 04)

