## BCL

High performance Cross-linked Shrink film



- Multi-layer, high clarity cross-linked Shrink film.
- Versatile film designed for a wide range of products.
- Strong seals on a wide range of sealing systems.
- High Tensile strength and tear resistance.
- Excellent machinability.



Bollore, Inc 60 Louisa Viens Drive Dayville, CT 06241 Sales: 800-343-0358 Fax: 888-700-8895 www.bolloreinc.com

## BCL

## High performance Cross-linked Shrink film

## Technical Features

Properties	125 Gauge	150 Gauge	
Yield (MSI/LBS)	24	20	
Gloss (45°) in %	86	85	
Haze (%)	4.2	5	
Free Shrink (%) @ 212° F @ 248° F	MD 16 MD 62	/	
Tensile Strength (psi)	19,580	19,580	
Elongation (%)	140	145	
WVTR (gm/100 sq. inch/24 hrs.)	.7	.6	
O <sup>2</sup> Permeability (cc/m <sup>2</sup> /24 hrs.)	4,200	3,300	
Roll Length (feet) Centerfold (CF) Singlewound (SW)	2,100 4,200	1,750 3,500	
Core Internal Diameter (inc	ch) 3	3"	
Nominal Outside Diameter	· (inch) 9	.5"	

Gauges	Centerfold	Singlewound
All	5 " to 55"	5" to 115"