

BOLPHANE® BTT+125

Thin Shrink Film suited for High Speed Machinery

BTT+125 is ideally suited for equipment where high speed packaging equipment is running. Exceptional shrink characteristics on irregular shaped items. **BTT+125** can be successfully used in applications ranging from multimedia to publishing items as well as office supplies

Advantages

- Enhanced stiffness for high speed machine compatibility.
- Instant Sealing.
- High shrink characteristics at low temperatures.
- Hot slip properties.
- Excellent optics & appearance.



The “Perfect Fit” for all your packaging film needs.





Technical Properties	Test Unit	Test Method		
			BTT+125	
Presentation				
Gauge			48	
Roll Length Singlewound	FT		11660	
Roll Length Centerfold	FT		5830	
Width Singlewound	in	Min: 4in Max: 78in Increment .25in		
Width Centerfold	in	Min: 5in Max: 40in Increment 1in		
Optical Properties				
Haze	%	ASTM D1003-A	114	
Gloss at 20°		ASTM D2457	118	
Shrinkage Properties			LD*	TD*
Free Shrink at 200°F	%	ATSM D2732	30	38
Free Shrink at 260°F			67	70
Mechanical Properties			LD*	TD*
Stiffness modulus	Mpa	ASTM D882	80000	87000
Elongation at break	%	ASTM D882	100	105
Tensile strength	PSI	ASTM D882	15600	15600
Barrier Properties				
Water vapor transmission rate (73 ⁰ F, 100% RH)	cc/100in ² /24hr/atm	ASTM E96	2.4	
O2 transmission rate (73 ⁰ F, 100% RH)	cc/100in ² /24hr/atm	ASTM D1434	850	

Contact Us

Give us a call for more information about our services and products

Bolloré Inc
60 Louisa Viens Drive
Dayville, CT 06241

1-800-343-0358

customer.service@bolloréinc.com

sales@bolloréinc.com

Visit us on the web at
www.bolloréinc.com