

BOLPHANE® BNAT-O

Sustainable Solution –Ultrathin multipurpose shrink film

Ultrathin display shrink film on the basis of a **green** polyethylene standard multipurpose. **B-Nat-O** is an ultrathin packaging shrink film developed on a basis of **green** polyethylene. It consists of more than **40%** of a polyethylene produced from a bio-source resin.

Besides coming from a renewable natural source, this **green** PE provides the same performances as a fossil polyethylene, can be recycled and contributes to minimizing the carbon footprint





The "Perfect Fit" for all your packaging film needs.

Advantages

- B-Nat-O is developed to offer the most attractive shelf presentation. Its optical properties are enhanced.
- Its cohesive strength makes it a good candidate for multi-packaging applications.
- The unique technical properties of B-NAT-O ensure excellent results on automatic high speed machines.









Technical Properties	Test Unit	Test Method		
			BNAT-O	
Presentation				
Gauge			60	
Roll Length Singlewound	FT		8750	
Roll Length Centerfold	FT		4375	
Width Singlewound	in	Min: 4in Max: 78in Increment .25in		
Width Centerfold	in	Min: 5in Max: 40in Increment 1in		
Friction Coefficients (Fi	lm to Film)			
Static		ASTM D1894	0.4	
Kinetic		A31W D1074	0.12	
Optical Properties				
Haze	%	ASTM D1003-A	3	
Gloss at 20°	70	ASTM D2457	114	
Shrinkage Properties			LD*	TD*
Free Shrink at 200°F	%	ATSM D2732	15	20
Free Shrink at 260oF			22	28
Mechanical Properties			LD*	TD*
Stiffness modulus	Mpa	ASTM D882	500	600
Elongation at break	%	ASTM D882	90	100
Tensile strength	PSI	ASTM D882	1000	1100
Barrier Properties				
	G/100in ² /24hr/atm		19	
Water vapor transmission rate 100°F, 95% RH)	aum	ASTM E96		
O2 transmission rate (73°F, 100% RH)	cm3/100in²/24 hr/ 1 atm	ASTM D1434	8000	

Contact Us

Give us a call for more information about our services and products

Bollore Inc 60 Louisa Viens Drive Dayville, CT 06241

1-800-343-0358

customer.service@bolloreinc.com

sales@bolloreinc.com

Visit us on the web at www.bolloreinc.com